



Glass Recommendations for Precision Molded Lenses

Preferred Glasses

Glass type ¹	n_d ²	v_d
K-PBK40	1.51760	63.5
K-CSK120	1.58699	59.5
K-VC79	1.61035	57.9
K-VC80	1.69384	53.1
K-VC82	1.75550	45.6
K-VC89	1.80998	41.0

1. Other glass types are possible – Contact your FISBA Sales Manager for for options and advice on cost and performance

2. Catalog values before molding – Contact your FISBA Sales Manger for more details on post molding performance

Glasses which are possible for specific lenses shapes

Glass type ¹	n_d^2	v_d
L-BAL42	1.58313	59.4
L-BAL35	1.58913	61.5
K-VC78	1.66955	55.4
K-LaFK50T	1.76600	49.8
K-LaFK50	1.77200	50.0

1. Other glass types are possible – Contact your FISBA Sales Manager for for options and advice on cost and performance

2. Catalog values before molding – Contact your FISBA Aales Manger for more details on post molding performance

Preferred Infrared glasses

Glass type ¹	n_d^2 @ 10 μ m	v_d @ 10 μ m
IG2 / IRG22	2.4968	111
IG3 / IRG23	2.7870	164
IG4 / IRG24	2.6091	179
IG5 / IRG25	2.6032	108
IG6 / IRG26	2.7781	159

1. Other glass types are possible – Contact your FISBA Sales Manager for for options and advice on cost and performance
2. Catalog values before molding – Contact your FISBA sales maanger for more details on post molding performance